

B-5021 HFO

B-5021 HFO / A-2732 is a ditch break polyurethane spray foam system specially formulated without any ozone depletion substances and has a Global Warming Potential (GWP) of 1, which is 99.9% lower than historical blowing agent. This system is designed to be built-up in thickness without scorching or foam splitting. This system is formulated with renewable and recycled products.

LED BY COMMITMENT



PREMIUM PRODUCT

Genyk uses the highest-grade raw materials and state-of-the-art manufacturing facilities. The result is a durable product with industry leading thermal resistance



SUSTAINABILITY

With its outstanding thermal performance and a GWP of 1, HFO blowing agent is a balanced solution to today's environmental and performance challenges in insulated foam applications.



LOCALLY REPRESENTED

Genyk is a Canadian manufacturer. Each region has local representation to offer the most knowledgeable service.

COMPONENT PROPERTIES		
PROPERTIES	ISOCYANATE A-2732	RESIN B-5021 HFO
Appearance	Brown liquid	Amber liquid
Viscosity @ 25°C	150 – 250 cps	200 - 300cps
Spécific Gravity @ 25°C	1.24	1.17 – 1.21
Shelf Life	12 months	6 months
Mixing Ratio (volume)	100	100

REACTIVITY PROFILE	
Cream Time (seconds)	0 - 1
Gel Time (seconds)	2 - 3
Tack Free Time (seconds)	4 – 5
Core Density (lb/ft3)	2.10

Laboratory results based on machine mixing (Graco E-30) at 110°F/1000psi. Properties shown below are to be used as a guide only and not intended for specification properties.

TYPICAL PHYSICAL PROPERTIES

Physical Properties	ASTM Method	Value
Core Density	D 1622	2.10 lb/pi3 (33.6 kg/m3)
Compressive Strength*	D 1621	31.0 psi (213.5 kpa)
Dimensional Stability	D2126 (7days, -25°C, ambient R.H)	-0.68%
	D2126 (7days, +80°C, ambient R.H)	3.47%
	D2126 (28 days +700C,97% +-3% R.H)	7.88%
Water Absorption (volume)	ASTM D2842	<1.0%
Initial Thermal Resistance	ASTM C518 (50mm)	7.15 ft2.h.0F/btu.in (1.26 m2.0C/W)

Properties shown below are to be used as a guide only and not intended for specification properties.

*Tested on panel sample prepared with 2 x 2-inch thickness per pass.



Genyk A-2732 is supplied in 227 kg drums and 1,250 kg totes. Genyk B-5021 HFO is supplied in 225 kg drums and 1,125kg totes.



Before handling these chemicals, please consult the Safety Data Sheet for the two components, that are available from Genyk.

STORAGE CONDITIONS AND HANDLING

All materials should be stored in their original containers and away from heat and moisture, especially after the seals have been broken and the containers have been opened. Shelf life is 6 months for the resin and 12 months for the isocyanate when stored indoors at a temperature between 60°F (15°C) and 77°F (25°C) for the resin and 60°F (15°C) and 100°F (38°C) for the isocyanate. Storage below 60°F (15°C) may result in compound stratification of the B and/or crystalline formation in the A component. Temperatures above the maximum storage temperatures may decrease the shelf life. Containers should be opened carefully to allow any pressure build-up to be vented safely. Extensive venting of the B component may result in loss of blowing agent, higher-density foam and reduced yield. Temperatures below 60°F (15°C) will increased the viscosity of the components making them difficult to pump. Both components are adversely affected by water and humidity.

ADDITIONAL INFORMATION

- This product is combustible and must be installed in accordance with applicable building codes.
- The service temperature is between -60°C and 85°C (-76°F and +185°F).
- Temperature, humidity, equipment, substrate can vary installation parameters.

The information contained herein is considered an accurate description of the product performance at the time of printing. Genyk Inc. disclaims any liability for incidental or consequential damages which may result from the inappropriate use of this product. It is the user's responsibility to thoroughly test the product in any application. No information contained herein is to be considered as permission or recommendation to infringe on any patent or other intellectual property.